



TGA Licence No:
MI-15112007-LI-002191-11

APVMA Licence No:
6139

AS/NZS 4020:2005 Compliance Testing

Certificate of Analysis
(Supersedes all interim reporting)
Dated: 05/09/2016

1. CERTIFICATE OF ANALYSIS AND SAMPLE INFORMATION:

Methodology: AS/NZS 4020, *Appendix A* and in-house method TMP-191100 & TMP-191101

Eurofins | ams Report Reference No.: 1614316

Cross Reference No.: NA

Submitting Organisation: EngPro Systems Pty. Ltd.


Contact: Nathan Spencer

Address: PO Box 790, Warners Bay, NSW 2282, Australia

Interim Reporting: NA

Project Completion Date: 05/09/2016

Product Designation: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea



Batch No./ Manufacturing Date: Refer to Attachment A

THIS REPORT MUST NOT BE REPRODUCED EXCEPT IN FULL

Page 1 of 10

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

Product Manufacturer:	Lockwell Systems Co. Ltd. 199/5 Moo 21, Soi Chongsiri Parkland, T. Bangpleeyai, A. Bangplee Samutprakarn 10540, Thailand
Sampling Organisation:	Lockwell Systems Co. Ltd.
General Composition:	Refer to attachments
Product Use:	In-Line
Temperature Range:	(-10 to 120)°C
Previous Testing:	NA
Date of receipt of samples:	16/06/2016
Sample selection for tests:	As provided by the Submitting Organisation
Sample storage conditions:	Prepared and controlled as per AS/NZS 4020, <i>Appendix A</i>
Extracts:	Prepared as per AS/NZS 4020, <i>Appendices C, D, E, F, G & H</i>
Testing procedure:	<p>Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea was applied to one side of a Stainless Steel panel with the dimensions of 120mm x 75mm x 1mm and exposure of ~9,000mm² / 1L. All test panels were prepared by Lockwell Systems Co. Ltd. (Refer to Attachment A). For testing, 2 x test panels were immersed in 1L of water to give a total testing exposure of ~18,000mm² / 1L.</p> <p>Testing is based on the recommended 'total immersion' exposure of ~18,000mm² / L test water at (20 ± 2)°C to cover a cold water application up to <40°C.</p> <p>Refer to Attachment A for Photo of test sample, Bill of Material (BOM), Technical Data Sheet (TDS) & Manufacturer's Declaration and Attachment B for Material Safety Data Sheets (MSDS).</p>
Volume retention:	NA

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

2. SUMMARY OF RESULTS:

APPENDIX	RESULTS
C - TASTE	PASS at testing exposure
D - APPEARANCE	PASS at testing exposure
E - GROWTH OF AQUATIC MICRO-ORGANISMS	PASS at testing exposure
F - CYTOTOXIC ACTIVITY	PASS at testing exposure
G - MUTAGENIC ACTIVITY	PASS at testing exposure
H - EXTRACTION OF METALS	PASS at testing exposure

Based on completion and evaluation of all tests on **05/09/2016**, the product, **Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea**; **fully complied** with the test requirements of **AS/NZS 4020:2005** to cover a cold water application up to **<40°C**, at the recommended 'total immersion' exposure of **~18,000mm² / L test water at (20 ± 2)° C**.

Testing although determined by the relevant product Standard, is generally recognised for up to 5 years by the certifying body, providing the testing procedures remain the same, and the background information on all wetted parts and the product are adequately documented. Also, the results stated in the report relate to the samples of the product submitted for testing. Any changes in the material formulation and supplier/manufacturer of all wetted items, the process of manufacture, the method of application, or the surface area-to-volume ratio in the end-use, could affect the suitability of the product for use in contact with drinking water, and re-testing may be required before this actual time frame, governed by the completion and evaluation date.

Signed:



SANDHYA L. SINGH B. Tech, Postgrad. Dip. (Chem)
Manager, Chemistry and Toxicology; Approved Signatory

Date: 05/09/2016

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

3. **TASTE OF WATER EXTRACT:**

Methodology: AS/NZS 4020, *Appendix C* and in-house method TMP-191130.

Exposure: 'total immersion'; ~18,000mm² / 1L test water

Extraction temperature: (20 ± 2)°C

Scaling factor: NA

Number of Panellists: 4

No. of samples for Chlorine-free extract: 2

No. of samples for Chlorinated extract: 2

Description	Extract	Test Water	Taste (+ / -)	Taste Description (No. of tasters)	Test Dilution *(Taste intensity)
Test Blank	First 24h	Chlorine-free	—	—	—
	Final 9-day	Chlorine-free	NA	NA	NA
Sample	First 24h	Chlorine-free	—	—	—
	Final 9-day	Chlorine-free	NA	NA	NA
Test Blank	First 24h	Chlorinated	—	—	—
	Final 9-day	Chlorinated	NA	NA	NA
Sample	First 24h	Chlorinated	—	—	—
	Final 9-day	Chlorinated	NA	NA	NA

+ Taste detected

— No taste detected

NA Not applicable

AS/NZS 4020 test requirement: Minimum of 4 tasters with no discernible taste at the first 1/2 dilution.

Figure in brackets is the number of panellists detecting a taste at this dilution.

Note:

1. Tasters are given a 14-point scale to describe its intensity, with minimum of 1 as extremely weak, and maximum of >14 as extremely strong. An average of all tasters represents taste intensity.
2. First extract becomes final extract.

EVALUATION:

On the basis of these results the samples of this product referred to in this report have complied with the test requirements of AS/NZS 4020:2005, Taste of Water Extract; *Appendix C*.

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

4. APPEARANCE OF WATER EXTRACT:

Methodology: AS/NZS 4020, *Appendix D* and in-house methods TMP-191140 and TMP-191106.

Exposure: 'total immersion'; ~18,000mm² / 1L test water

Extraction temperature: (20 ± 2)°C

Scaling factor: NA

No. of samples tested: 2

	a) TRUE COLOUR: Hazen Units (HU)		b) TURBIDITY: Nephelometric Turbidity Units (NTU)	
	First 24h	Final 9-day	First 24h	Final 9-day
Sample Extract pH = 5.53	2.5	NA	0.25	NA
Test Blank pH = 5.61	2.0	NA	0.13	NA
FINAL RESULT	0.5	NA	0.12	NA
AS/NZS 4020 Test sample requirements	≤5		≤0.5	

< = less than

≤ = less than or equal to

NA Not applicable

First extract becomes final extract

For test a), test extractions were performed by Eurofins ams Laboratories Pty. Ltd. The test extracts were subsequently subcontracted to Eurofins | mgt for assessment (NATA Accreditation No. 1261), Report No. 505472-W.

EVALUATION:

On the basis of these results the samples of this product referred to in this report have complied with the test requirements of AS/NZS 4020:2005, Appearance of Water Extract; *Appendix D*.

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

5. **GROWTH OF AQUATIC MICRO-ORGANISMS:**

Methodology: AS/NZS 4020, *Appendix E* and in-house method TMP-191150.

Incubation temperature: (30 ± 1)°C

Exposure: 'total immersion'

Component Name	Testing Exposure	Inoculum (mL)	* MEAN DISSOLVED OXYGEN DIFFERENCE (MDOD) in mg/L
i) Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	~18,000mm ² (2 panels) / 1L	100	0.36
ii) Stainless Steel Blank Panel	~18,000mm ² (1 panel) / 1L	100	NA
Negative Reference Control (glass plate)	~15,000mm ² / 1L	100	<0.01
Positive Reference Control (paraffin waxed glass plate)	~15,000mm ² / 1L	100	9.51
Test Blank	Blank / 1L	100	7.07 in mg/L as mean dissolved oxygen

NA Not applicable

* Difference from test blank and represents mean of triplicate readings (weeks 5, 6, 7)

AS/NZS 4020 test sample requirements: Less than or equal to 2.4 for MDOD

EVALUATION:

On the basis of these results the samples of this product referred to in this report have complied with the test requirements of AS/NZS 4020:2005, Growth of Aquatic Micro-organisms; *Appendix E*.

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

6. CYTOTOXIC ACTIVITY OF WATER EXTRACT:

Methodology: AS/NZS 4020, *Appendix F* and in-house method TMP-191160.

Exposure: 'total immersion'; ~18,000mm² / 1L test water

Extraction temperature: (20 ± 2)°C

Scaling factor: NA

Extracts: 24h, 48h & 72h

No. of samples tested: 2

The test sample extracts from the product, as well as the test blank (test water) were used to prepare a nutrient growth medium, subsequently utilised to grow a monkey kidney cell line (VERO ATCC CCL 81).

Microscopic Examination	Test Sample Extract (24h, 48h and 72h)	Test Blank (24h, 48h and 72h)
Cell Morphology:	Satisfactory	Satisfactory
Monolayer: Confluence/Healthy Growth as ~%	100%	100%

Cytotoxicity was detected with zinc sulphate, used as a positive control and analysed at 4µg/g, 8µg/g and 16µg/g of zinc. Water for Irrigation, Synthetic Water for Irrigation, and Phosphate Buffer Solution were included with the test blank as negative controls.

AS/NZS 4020 test sample requirements: 1) Non-cytotoxic response- confluent monolayer similar to test blank.

2) Cytotoxic response- irregularly shaped cells & cell death similar to positive controls of 8µg/g & 16µg/g zinc sulphate.

EVALUATION:

On the basis of these results the samples of this product referred to in this report have complied with the test requirements of AS/NZS 4020:2005, Cytotoxic Activity of Water Extract; *Appendix F*.

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

7. MUTAGENIC ACTIVITY OF WATER EXTRACT:

Methodology: AS/NZS 4020, *Appendix G* and in-house method TMP-191170.

Exposure: 'total immersion'; ~18,000mm² / 1L test water

Extraction temperature: (20 ± 2)°C

Scaling factor: NA

Extract: 24h

No. of samples tested: 2

BACTERIAL STRAIN: <i>Salmonella typhimurium</i>	* S9 -No +With	a) TRIPLICATES (REVERTANTS/PLATES) b) MEAN ± STANDARD DEVIATION			
		TEST BLANK (Extractant Water)	SAMPLE EXTRACT (Leachate)	NEGATIVE CONTROL (Test culture only)	POSITIVE CONTROL (Standard diagnostic mutagen)
TA 98	-	a) 28 51 49	a) 35 38 54	a) 43 44 40	a) IV 2,640 1,750 2,820
		b) 43 ± 13	b) 42 ± 10	b) 42 ± 2	b) 2,403 ± 573
TA 98	+	a) 61 65 58	a) 100 92 90	a) 159 153 150	a) IV 2,910 2,820 2,500
		b) 61 ± 4	b) 94 ± 5	b) 154 ± 5	b) 2,743 ± 215
TA 100	-	a) 505 466 494	a) 455 467 485	a) 443 405 400	a) II 20,590 23,260 20,200
		b) 488 ± 20	b) 469 ± 15	b) 416 ± 24	b) 21,350 ± 1,666

* Metabolic Activator
II = sodium azide

NA = Not applicable
III = Benzo(a)pyrene

> = greater than
IV = 2-aminoanthracene

I = 2, 4-dinitrophenylhydrazine

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

BACTERIAL STRAIN: <i>Salmonella typhimurium</i>	* S9	a) TRIPLICATES (REVERTANTS/PLATES) b) MEAN ± STANDARD DEVIATION			
	-No	TEST BLANK	SAMPLE EXTRACT	NEGATIVE CONTROL	POSITIVE CONTROL
	+With	(Extractant Water)	(Leachate)	(Test culture only)	(Standard diagnostic mutagen)
TA 100	+	a)	a)	a)	a)
		493	412	401	III
		454	464	400	5,670
		500	463	412	5,600
TA 102	-	b)	b)	b)	b)
		482	446	404	5,777
		± 25	± 30	± 7	± 248
TA 102	+	a)	a)	a)	a)
		864	858	768	I
		800	740	774	8,000
		767	802	700	9,200
TA 102	-	b)	b)	b)	b)
		810	800	747	8,133
		± 49	± 59	± 41	± 1,007
TA 102	+	a)	a)	a)	a)
		923	812	511	IV
		792	737	547	5,020
		736	700	500	5,000
TA 102	-	b)	b)	b)	b)
		817	750	519	5,200
		± 96	± 57	± 25	± 110

* Metabolic Activator NA = Not applicable > = greater than I = 2, 4-dinitrophenylhydrazine
II = sodium azide III = Benzo(a)pyrene IV = 2-aminoanthracene

AS/NZS 4020 test sample requirements: (The differences in the mean number of revertants between either of the negative controls and test sample extracts should not exceed two standard deviations (for triplicate analysis)).

Positive response: If mean revertants for sample extract outside the range of spontaneous revertants for test strain.

EVALUATION:

On the basis of these results the samples of this product referred to in this report have complied with the test requirements of AS/NZS 4020:2005, Mutagenic Activity of Water Extract; *Appendix G*.

Eurofins ams Laboratory Final Report for the testing of a product to AS/NZS 4020, Products for use in contact with Drinking Water	Eurofins ams Report No.: 1614316
Submitting Organisation: EngPro Systems Pty. Ltd.	
Product: Lockwell P601 Epoxy Primer under Lockwell P515 Pure Polyurea	Date of Report: 05/09/2016

8. EXTRACTION OF METALS:

Methodology: AS/NZS 4020, *Appendix H* and in-house methods TMP-191180 and TMP-191230.

Exposure: 'total immersion'; ~18,000mm² / 1L test water

Extraction temperature: (20 ± 2)°C

Scaling factor: NA

Extracts: 24h

No. of samples for I: 2

No. of samples for II: 2

Element	AS/NZS 4020: Maximum Allowable Concentration mg/L (ppm)	Limit of Reporting mg/L (ppm)	Test Blank mg/L (ppm)	Sample Extract I mg/L (ppm)	Sample Extract II mg/L (ppm)	FINAL RESULT I mg/L (ppm)	FINAL RESULT II mg/L (ppm)
antimony ¹ (Sb)	0.003	0.0001	0.0002	0.0001	0.0001	<0.0001	<0.0001
Arsenic ¹ (As)	0.007	0.0002	<0.0002	<0.0002	<0.0002	<0.0002	<0.0002
barium ¹ (Ba)	0.7	0.0001	0.0014	0.0008	0.0009	<0.0001	<0.0001
cadmium ¹ (Cd)	0.002	0.00005	<0.00005	<0.00005	<0.00005	<0.00005	<0.00005
chromium ¹ (Cr)	0.05	0.0002	<0.0002	<0.0002	<0.0002	<0.0002	<0.0002
copper ¹ (Cu)	2	0.0004	0.0005	0.0005	0.0006	<0.0004	<0.0004
lead ¹ (Pb)	0.01	0.0001	0.0008	0.0006	0.0007	<0.0001	<0.0001
Mercury ¹ (Hg)	0.001	0.0001	<0.0001	<0.0001	<0.0001	<0.0001	<0.0001
molybdenum ¹ (Mo)	0.05	0.005	<0.005	<0.005	<0.005	<0.005	<0.005
nickel ¹ (Ni)	0.02	0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005
Selenium ¹ (Se)	0.01	0.0002	0.0005	0.0003	0.0003	<0.0002	<0.0002
silver ¹ (Ag)	0.1	0.0001	<0.0001	<0.0001	<0.0001	<0.0001	<0.0001

< = less than mg/L = milligram per litre ¹ = ICPMS – In-house Method Code: LTM-MET 3040
First extract becomes final extract.

Test extractions were performed by Eurofins ams Laboratories Pty. Ltd. The test extracts were subsequently subcontracted to Eurofins | mgt for assessment (NATA Accreditation No. 1261), Report No. 505472-W.

EVALUATION:

On the basis of these results the samples of this product referred to in this report have complied with the test requirements of AS/NZS 4020:2005, Extraction of Metals; *Appendix H*.